

REMARKS/ARGUMENTS

Claims 1 and 8 have been amended. Claims 6, 7, 9, 10, and 13 have been canceled, applicants reserving the right to file one or more divisional applications on the deleted subject matter.

The objection to the drawings is believed obviated by cancellation of claims 6, 7 and 13.

The objection to the specification is obviated by submission of a substitute specification rearranged in accordance with the Examiner's instructions. Applicants have stated that there is no new matter.

Applicants respectfully traverse: the rejection of claims 1 – 5, 8, 11 and 12, and 17 under 35 U.S.C. 102(b) as anticipated by Ebbinghaus et al; the rejection of claims 1 – 5, 8, 11 and 12, 14, 16, and 17 under 35 U.S.C. 102(b) as anticipated by Suzuki; and the rejection of claim 15 under 35 U.S.C. 103(a) as unpatentable over Suzuki.

The hollow camshaft structure of Suzuki is entirely different from the present camshaft in that Suzuki teaches to expand the hollow tube in the areas not covered by cams and other elements, but only in the spaces in between. In this respect, please refer to Fig. 5 and Fig. 11, especially items 2a and 9.

Current claim 1 of the present invention requires the tube to be expanded to defined regions form hollow cams, which means that the cams are formed out of the tube. The rings applied to the tube are bearer rings, not cam rings, because their only purpose is to provide a surface having the necessary harness, strength and wear resistance.

As can be seen from Suzuki, the hollow tube is mostly straight and has its narrow parts in exactly those places, were the cams and other elements are placed. In this respect, please also refer to the description of Fig. 11, in particular the passage in column 6, lines 36 to 53 stating "that the parts of the hollow shaft protrudingly expand(ed) outward at the side faces of the disks 3... ."

Thus, Suzuki is not suited to teach the formation of hollow cams in a camshaft by expansion of the tube.

Ebbinghaus et al., also lack the teaching of the cam formation out of a tube. As can be seen from Fig. 1, the hollow shaft is expanded at the sides, where the secondary shaping elements are located. However, the expansion is such that only a non-rotary connection takes place between the shaft and the structure element, see col. 3, lines 63 to 65. Ebbinghaus et al., do not teach the widening of a tube by applying internal pressure in order to form hollow cams, such as are shown in Fig. 1 of the present application, but only the fixation of cam rings on a tube.

According to the present invention, the cams are formed out of the hollow tube. The bearer rings have not the function of cam rings, but only provide a hardened surface. The internal pressure widening process requires the material of the tube to be relatively soft and shapable. The soft material, however, cannot withstand the forces applied to the surface of cams. Therefore, bearer rings having the necessary hardness, strength and wear resistance are applied. The bearer rings are not required to have uneven wall thickness, as shown in Fig. 2 of the '268 patent. In fact, for commercial reasons, the bearer rings are shaped cut-offs of hardened tubes with even wall thickness as required by the claims. The embodiment of present Fig. 5 with an increased thickness near the cam tip is for special purposes only and has no specific commercial interest.

Applicants believe the claims are in condition for allowance and respectfully solicit a Notice of Allowance.

A Petition for Extension of time is also enclosed.

Respectfully submitted,

A handwritten signature in black ink, appearing to be 'Robert Berliner', is written over a large, horizontal, oval-shaped scribble or stamp.

Robert Berliner
Registration No. 20,121

Date: March 5, 2004 ...
(213) 892-9237 (direct dial)



MARKED UP VERSION

RECEIVED
MAR 15 2004
GROUP 3600

TITLE OF THE INVENTION

A method production of cam shafts and a cam shaft produced by the method
Method For Production Of Cam Shafts And A Cam Shaft Produced By The
Method

CROSS-REFERENCE TO RELATED APPLICATIONS

Not Applicable

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

Not Applicable

INCORPORATION-BY-REFERENCE OF MATERIALS SUBMITTED ON A COMPACT DISC

Not Applicable

BACKGROUND OF THE INVENTION

Field of the Invention

The field of the invention is camshafts.

Description of Related Art including information disclosed under 37 CFR 1.97 and 1.98.

~~The invention relates to a method for the production of cam shafts and to a cam shaft produced by way of said method. It is preferably a question of cam shafts for engines for motor vehicles, although the method is also suitable for the production of similar products such as shafts having cams on them for other applications than engines. Such cams would then be elements for converting rotary movement into a linear one, the linearly moving elements~~

~~running on cams having different curvatures and able to moved against the direction of rotation.~~

[0001] Cam shafts are known which are produced integrally, that is to say forged or cast. Following a mechanical machining operation, the running faces of the cams, which are subject to wear, are hardened by laser rays, electron beams or WiG remelted or, for example, hardened inductively or in a thermal/chemical process. After there is further machining, for example grinding the bearings and the shape of the cams. These cam shafts suffer from the disadvantage that their weight and accordingly the mass to be moved is extremely high. The great mass of the cam shaft has a disadvantageous effect on fuel consumption. A further disadvantage is the intensive machining for processing the blank.

[0002] It is furthermore known to produce cam shafts from a plurality of parts. The individual cams are placed on the shaft and preferably secured thereto by welding, swaging or shrinking. In this respect it is possible to overcome the disadvantage of the substantial weight of solid, integral cams, for the shaft can be a hollow shaft, but production is extremely complex.

[0003] In accordance with a further known method the individual cams are secured to hollow shaft by causing expansion of the hollow shaft, with the individual cams slipped onto it, by the action of pressure. As a pressure medium use is preferably made of a liquids. The pressure is supplied by way of a piston or stamp (see German patent publications 3,409,541 and 3,521,206). This method does however suffer from the disadvantage that the production of the individual parts, and more particularly fitting together, is technologically extremely complex and the internal shape of the cams is limited.

[0004] It is furthermore known to produce cam shafts by producing an elongated hollow body, that is to say a hollow shaft, by internal pressure forming method (IHU method) so that the material is thrust outward as cams individually, in sequence or simultaneously.

[0005] Suitable two-part or four-part tools are employed to feed the hollow shaft in the axial direction to ensure that the cams are produced at

predetermined positions and forming in an integral manner takes place (WO 97/46341).

[0006] The cam shaft produced by this method does however suffer from the disadvantage that although the costs of manufacture are less than with forged cam shafts or those produced from a plurality of parts, the resistance to wear of the cam faces is unsatisfactory. It is impossible to employ the IHU-method on a sufficiently wear resistant material. It is not possible to produce an even running face on the cams in the case of a small spacing between the cams, as is normally the case with motor vehicle cams, for at the points of maximum forming the material is necessarily weakened, and thus strength is unfavorably affected.

[0007] If a material is employed for the hollow shaft, which contributes to reducing such shortcomings, it will admittedly allow adequate forming, but the hardness or, respectively, wear resistance can not be achieved, even with a subsequent hardening step. It is however the hardness and wear resistance of the cams which is a basic requirement for a long working life of a cam shaft in a motor vehicle engine. It is also extremely hard, or even impossible, to achieve the necessary material thickness everywhere in the cam shaft, that is to say the shaft itself and more particularly the flanks and tips of the cams.

[0008] It is furthermore known to produce the tube sections constituting the cam face with an eccentric profile and to reinforce it by producing a press fit connection. The production of the cam takes place using explosion forming. The individual cams are secured to the cam shaft with a suitable offset in relation to one another (East German patent publication 234,223). Cam shafts currently produced by the method entail complex manufacture and are heavy. The timing of the plastic forming process is not able to be controlled.

BRIEF SUMMARY OF THE INVENTION

[0009] The invention relates to a method for the production of cam shafts and to a cam shaft produced by way of said method. It is preferably a question of cam shafts for engines for motor vehicles, although the method is also suitable for the production of similar products such as shafts having cams

on them for other applications than engines. Such cams would then be elements for converting rotary movement into a linear one, the linearly moving elements running on cams having different curvatures and able to moved against the direction of rotation.

[0010] One object of the invention is to provide a method for the production of cam shafts, with which by using the known high internal pressure forming method cam shafts may be produced, which have adequate strength, have low flexure, possess a high resistance to torsion and possess high flexural strength in the loaded faces of on the cam flank and tips or crests. The method of manufacture is to be simple. The application of an additional layer, that is to say an anti-wear layer in a further process step, and furthermore complex later machining is not to be necessary. The amount of material used is to be low. The number of the necessary separate parts for the entire cam shaft is to be reduced in comparison known methods of manufacturing cam shafts.

[0011] In accordance with the invention this object is to be attained ~~with the features of claim 1 and 8. Advantageous further features are described in claims 2 through 7 and furthermore claims 9 through 17.~~ by a method for the manufacture of a cam shaft from a tube, which is deformed by the action of axial forces and a medium under a high internal pressure, characterized in that the bearer rings, which are produced in a separate method and correspond to the outline of the cams, the desired hardness, strength and resistance to wear, are placed in a high internal pressure forming tool together with the tube to be formed and in that by the action of axial forces and a medium under a high internal pressure the bearer rings are attached by expansion of the tube in a frictional and interlocking manner.

[0012] The cam shaft is so produced from a tube by an internal high pressure forming method that the shaft complies peripherally to have all cams in form and in position in a single piece, that on the formed cams a bearer ring, shaped to correspond to the cam periphery and made of a hard, wear-resistant material is secured frictionally and in an interlocking manner, on

which in a known manner bearing elements and/or drive elements and/or control elements are arranged.

[0013] The method is characterized in that in a first method step prior to such high internal pressure forming, certain region, preferably ends of the tube, which are clear of the region, in which the cams are seated, are so kneaded and/or upset that same are increased in thickness and/or are stretched and thus different functional elements are formed. Between the cam shaft ends in the first method step prior to internal high pressure forming bearing faces and the eventual region where the cams are to be seated, are produced round kneading by reducing the diameter in this part to the desired size. Cams bearing faces are produced by internal high pressure forming by expanding the tube. The bearer rings are hardened in a known manner prior to being placed in the internal high pressure forming tool. A gear wheel or sprocket wheel produced in a separate method is placed in the internal high pressure forming tool and is connected by the internal high pressure forming step frictionally and/or in an interlocking manner. After the production of the thickened and/or tapered ends of the cam shaft, internal gear teeth and/or a thread is produced by round kneading integrated in an additional method step as part of this method step.

[0014] In one embodiment, a cam shaft produced as set forth above is characterized in that the bearer rings possess the same wall thickness. In another embodiment, a cam shaft produced as set forth above is characterized in that the thickness of the bearer rings is variable, the thickness being greatest near the cam tip.

[0015] In a further embodiment, a cam shaft produced as set forth above is characterized in that the bearer ring is produced of sintered metal, or plastic or ceramic material. The tube can be produced of aluminum, magnesium or titanium or its alloys. The ends of the tube can be formed by kneading so that by expansion or tapering the original diameter (D_i and d_a) of the tube possesses bearing faces, drive and/or control elements and internal and/or external screw threads. The drive and control elements, preferably sprocket or gear wheels, can be produced by an internal high pressure

forming method. At least one radially extending groove can be produced in the bearer ring and the drive and control elements. In another embodiment, the side, facing the tube of the bearer ring has chamfers on one or both sides on the side facing the tube. In a still further embodiment, a cam shaft produced as set forth above is characterized in that the bearer ring is hardened prior to application on the formed cams.

[0016] The essence of the invention is that suitably hard and wear-resistance bearer rings with thin walls and having the eventual form of the cam are produced, such bearer rings are inserted in an IHU tool by high internal pressure forming (referred to as IHU) and using the axial forces applied to the tube in combination with internal forces applied by way of a pressure medium a single or double stage forming of the tube takes place to yield the cam shaft.

[0017] At the end of the forming process the frictional and interlocking connection of the cam with the bearer ring takes place. At the ends of the cam shaft known bearing elements or journals are arranged and then secured in a known fashion.

[0018] In accordance with a further preferred development of the invention in a method step, which precedes the above mentioned method, a tube of a material satisfying the necessary requirements for forming and as regards mechanical properties, is so deformed by the known method of kneading, also known as roll kneading, or swaging, that the tube, completely or partially, or only the cam shaft ends, is plastically formed, that is to say for instance stretched and/or made thicker. At the ends shaped elements for drive and control elements, for instance the seat for gear wheels are produced. In the following the above mentioned method step the IHU method is used to flare out the tube that region, in which the cams are arranged, the IHU tool having been previously had the bearer rings inserted into it in accordance with the positions of the cams.

[0019] In the case of cams which have a very sharp curvature there is the disadvantage, when the bearer rings have a constant wall thickness, that the tube is subject to a high degree of deformation and in some cases a multi-

stage forming method will be necessary. This leads to an increase in manufacturing costs and a reduction in productivity. Furthermore in the cylinder head there are interfering structures clear of the cam shaft and between or alongside the cams. They mean that the space available is reduced and the IHU process is harder to perform. This limitation is only, if at all to be overcome by the use of a complicated, multi-stage IHU process. This in turn leads to high costs of production. Therefore an advantageous form of the method and, respectively, of the shaft produced in it, is such that the bearer rings, which are produced in a separate method, externally possess the functionally dependent outline and internally have and somewhat greater diameter than the tube. The wall thickness of the bearer ring is not constant and is greater at the cam tip or crest. This means that the bearer ring has, as a cam, a variable thickness and its inner periphery is not a circle.

[0020] The method in accordance with the invention is essentially that two or more modern manufacturing methods are combined with each other.

[0021] It is an advantage to produce at least one groove radially in the bearer ring in order to prevent displacement of the bearer ring because during the action of pressure such groove becomes filled with material of the shaft.

[0022] An other preferred feature of the invention is such that the drive and/or control elements are also secured on the shaft using the IHU method. Furthermore bearing faces may be produced by expansion of the tube using the IHU method as well. The cold solidification or hardening of the tube material owing to the plastic displacement process is particularly advantageous.

[0023] The cam shaft produced in accordance with method of the invention is extremely light in weight owing to the hollow cams and very thin walled bearer rings and has a high degree of stiffness. The the advantage that the the bearer rings at the most only have to be machined to a minor extent. Their hardness meeting requirements is already provided, this meaning that later hardening, which is normally necessary, for example inductive hardening or remelting hardening in a vacuum process, can be dispensed with.

[0024] Further development of the method leads to the additional advantage that the round kneading or upsetting in combination with the IHU method - unlike the case with all other manufacturing methods - only involves very low manufacturing complexity and consequently low costs. The costs are more especially reduced because the number of individual parts to be separately manufactured and then to be fitted is extremely low. Owing to manufacture in accordance with the invention sources of error are minimized, which so far occurred in the fitting together of parts so far practiced. A substantial advantage of the method is due to the fact that the kneading method renders possible the production of functional elements, which as regards their geometry, dimensional accuracy and surface quality require very little additional machining. Frequently only a grinding process is necessary to finish them.

[0025] The cam shaft produced in the method of the invention has a small number of separate parts. At the end of the forming process the cam rings are connected with the shaft frictionally and in an interlocking manner.

[0026] It is advantageous as well to provide the bearer ring on the side facing the tube on one or both sides with a chamfer. This furthermore prevent lateral displacement on the shaft.

[0027] An advantageous design of the bearer rings is such that the bearer ring, as in the prior art, consists of plastics or sintered materials. Such materials offer the advantage of simple manufacture with low manufacturing costs.

[0028] Furthermore ceramic materials may be utilized. They bring the advantage of maximum wear resistance and minimum weight so that very light cam shafts may be produced.

[0029] The invention will now be described with reference to two working examples illustrated in the accompanying drawings.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0030] Figure 1 shows a longitudinal section taken through a finished cam shaft.

Figure 2 shows a cross section taken through a cam on the shaft.

Figure 3 shows part in longitudinal section taken through a cam on the shaft.

Figure 4 shows a cam shaft formed by round kneading/upsetting.

Figure 5 shows a cam shaft with bearer rings of non-constant thickness in section.

DETAILED DESCRIPTION OF THE INVENTION

[0031] Figures 1 through 3 show the manufacture of a cam shaft in the IHU method.

[0032] By IHU forming in a pressing mold a cam shaft is produced from a thin walled tube 1 of readily deformable material so as to comply with contours, that is to say the positions where a cam is to be seated are deformed outward in accordance with the dimensions of the cam 2 and its position. The shaft with its cam 2 is a single hollow body. In a known process bearer rings 3, as shown in figures 2 and 3, are manufactured. For this purpose a tube of wear-resistant material is so shaped that the eventual form of the bearer ring 3 (cam) is set and the ring is hardened. The prefabricated tube 1, which is to be formed to constitute the cam shaft, is thrust through the bearer rings 3 and together with them placed in the opened forming tool. All individual parts are therefore locked in position. The forming tool is closed axial and the force for forming may be applied. The application of force starts with a predetermined axial force on the tube 1 and/or the tool, supported by a predetermined internal pressure in the tube 1. After completely closing the tool further operations are performed with an orthodox IHU process to connect the tube 1 and the bearer ring 3 by friction and by an interlock. Bearing or drive elements 5 are arranged in a known manner on the end of the tube 1. It is also possible to secure same to the tube 1 using the IHU method as well.

[0033] It is furthermore possible to provide a groove 4 in the interior of the bearer ring 3 so that the hold of the cam 2 is improved since the groove becomes filled with the material of the tube 1. It is also possible to provide the

bearer ring with chamfers which are filled with material during following IHU method.

[0034] The manufacture of a cam shaft by the IHU method in combination with the kneading method will now be described in a further example on the basis of figure 4.

[0035] The tube 1 of a readily deformed material is deformed at its ends by round kneading or upsetting to increase its thickness. On one side its internal diameter D_1 is thus reduced and its external diameter D_A is defined so that a zone 6 reinforcing the cam shaft is produced. At the outer end a functional element 7 is produced, whose seat is sized by grinding. At the other end again by kneading or upsetting the internal diameter D_1 of the end already described is reduced simultaneously and a further functional element 7 (bearing seat, cam etc.) is created. In the following method step a collar 8 is produced by upsetting as well which is required for the flank mounting of other components.

[0036] After the first method stage the bearer rings 3, produced in a separate process, which correspond to the shape of the cams and the sprocket (not illustrated) are mounted by the IHU method frictionally and with an interlocking effect. For this purpose the bearer rings 3 and the sprocket are placed in the IHU tool.

[0037] Figure 5 shows a design of the cam shaft in which the bearer ring 3 has a varying thickness.

[0038] The tube 1 of a readily deformable material has an external diameter d_a . The bearer ring 3 of sintered metal has an outer form as dictated by function and internally is not circular. Its internal diameter D_i is somewhat larger than the external diameter d_a of the tube 1. The thickness of the bearer ring 3 is not constant. The height A , which would result if one were to assume a constant thickness of the bearer ring, is larger than the height A of the maximum displacement of the tube 1 and thus the radius R_i at the deformation of the tube 3 is larger than R ; assuming an equal thickness c' of the bearer ring 3. In this part the thickness c of the bearer ring 3 is larger and extends into the part with a constant thickness c .

[0039] Even although in this form the bearer ring 3 is slightly more expensive, the reduced costs of the IHU method are significant on balance, such method being possible in one step.

CLAIMS

1. A method for the manufacture of a cam shaft from a tube, which can be deformed by the action of axial forces and a medium under an internal pressure, characterized in that bearer rings, produced in a separate method and corresponding to the outline of the cams on said cam shaft, are placed in a high internal pressure forming tool together with the tube to be formed and subjected to the action of axial forces and a medium under a high internal pressure, whereby the bearer rings are attached by expansion of the tube in a frictional and interlocking manner.

2. The method as set forth in claim 1, characterized in that in a first method step prior to such high internal pressure forming, regions that lie outside the regions in which the cams are seated, are so kneaded and/or upset that same are increased in thickness and/or are stretched and thus different functional elements are formed.

3. The method as set forth in claim 1, characterized in that between the cam shaft ends in the first method step prior to internal high pressure forming bearing faces and the eventual region where the cams are to be seated, are produced round kneading by reducing the diameter in this part to the desired size.

4. The method as set forth in claim 1 or in claim 2, characterized in that between cams bearing faces are produced by internal high pressure forming by expanding the tube.

5. The method as set forth in ~~at least one of the claims 1 through 4~~ claim 1, characterized in that the bearer rings are hardened in a known manner prior to being placed in the internal high pressure forming tool.

6. The method as set forth in ~~at least one of the claims 1 through 5~~ claim 1, characterized in that a gear wheel or sprocket wheel produced in a separate method is placed in the internal high pressure forming tool and is connected by the internal high pressure forming step frictionally and/or in an interlocking manner.

7. The method as set forth in ~~at least one of the claims 1 through 6~~ claim 1, characterized in that after the production of the thickened and/or tapered ends of the cam shaft internal gear teeth and/or a thread is produced by round kneading in an additional method step integrated in an additional method step as part of this method step.
8. A cam shaft produced as set forth in claim 1, characterized in that the cam shaft is so produced from a tube (1) by an internal high pressure forming method that the shaft complies peripherally to have all cams (2) in form and in position in a single piece, that on the formed cams (2) a bearer ring (3), shaped to correspond to the cam periphery and made of a hard, wear-resistant material is secured frictionally and in an interlocking manner, on which in a known manner bearing elements and/or drive elements and/or control elements (5) are arranged.
9. A cam shaft produced as set forth in claim 8, characterized in that the bearer rings (3) possess the same wall thickness.
10. A cam shaft produced as set forth in claim 8, characterized in that the thickness of the bearer rings (3) is variable, the thickness being greatest near the cam tip.
11. A cam shaft produced as set forth in claim 8, characterized in that the bearer ring (3) is produced of sintered metal, or plastic or ceramic material.
12. A cam shaft produced as set forth in claim 8, characterized in that the tube (3) is produced of aluminum, magnesium or titanium or its alloys.
13. A cam shaft produced as set forth in claim 8, characterized in that the ends of the tube (3) are formed by kneading so that by expansion or tapering the original diameter (D_i and d_a) of the tube (1) possesses bearing faces, drive and/or control elements and internal and/or external screw threads.
14. A cam shaft produced as set forth in claim 8, characterized in that the drive and control elements, preferably sprocket or gear wheels, are produced by an internal high pressure forming method.

15. A cam shaft produced as set forth in claim 14, characterized in that at least one radially extending groove (4) is produced in the bearer ring (3) and the drive and control elements.

16. A cam shaft produced as set forth in claim 14, characterized in that the side, facing the tube (1) of the bearer ring (3) has chamfers on one or both sides on the side facing the tube (1).

17. A cam shaft produced as set forth in claim 8, characterized in that the bearer ring (3) is hardened prior to application on the formed cams.

ABSTRACT OF THE DISCLOSURE

[0040] A method for the production of cam shafts, with which by using the known high internal pressure forming method cam shafts may be produced, which have adequate strength, have low flexure, possess a high resistance to torsion and possess high flexural strength in the loaded faces of on the cam flank and tips or crests.

SEQUENCE LISTING

Not Applicable